



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01J 31/02, 37/00, 29/06, C01B 39/02	A1	(11) International Publication Number: WO 00/56450 (43) International Publication Date: 28 September 2000 (28.09.00)
(21) International Application Number: PCT/US00/07684 (22) International Filing Date: 20 March 2000 (20.03.00) (30) Priority Data: 09/272,762 19 March 1999 (19.03.99) US Not furnished 17 March 2000 (17.03.00) US (71) Applicant: BATTELLE MEMORIAL INSTITUTE [US/US]; Pacific Northwest Division, Intellectual Property Services, P.O. Box 999, Richland, WA 99352 (US). (72) Inventors: FRYXELL, Glen, E.; 8907 W. Entiat Avenue, Kennewick, WA 99336 (US). ZEMANIAN, Thomas, S.; 505 Jadwin Avenue, Richland, WA 99352 (US). LIU, Jun; 5656 Collins Road, West Richland, WA 99353 (US). SHIN, Yongsoon; 1151 Dos Palos Court, Richland, WA 99352 (US). (74) Agent: MAY, Stephen, R.; Battelle Memorial Institute, Pacific Northwest Division, Intellectual Property Services, P.O. Box 999, MSIN: K1-53, Richland, WA 99352 (US).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>	
(54) Title: SELF-ASSEMBLED MONOLAYER AND METHOD OF MAKING		
(57) Abstract <p>According to the present invention, the previously known functional material having a self-assembled monolayer on a substrate has a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites (four sites when silicon is the assembly molecule) wherein a bonding fraction (or fraction) of fully bonded assembly atoms (the plurality of bonding sites bonded to an oxygen atom) has a maximum when made by liquid solution deposition, for example a maximum of 40 % when silicon is the assembly molecule, and maximum surface density of assembly molecules was 5 silanes per square nanometer. Note that bonding fraction and surface population are independent parameters. The method of the present invention is an improvement to the known method for making a siloxane layer on a substrate, wherein instead of a liquid phase solution chemistry, the improvement is a supercritical phase chemistry. The present invention has the advantages of greater fraction of oxygen bonds, greater surface density of assembly molecules and reduced time for reaction of about 5 minutes to about 24 hours.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

SELF-ASSEMBLED MONOLAYER AND METHOD OF MAKING

5

FIELD OF THE INVENTION

The present invention is a self-assembled monolayer and method of making.

10

BACKGROUND OF THE INVENTION

Since their unveiling in 1992, mesoporous ceramics have inspired substantial interest, especially by adding self-assembling monolayer compounds to the surface(s) of the mesopores. By varying the terminal group of the self-assembling monolayer, various chemically functionalized materials have been prepared. A mesoporous material is defined as a material, usually catalytic material, having pores with a diameter or width range of 2 nanometers to 0.05 micrometers.

Exemplary of use of self-assembling monolayer(s) on a mesoporous material is the International Application Publication WO '98/34723 (E-1479 CIP PCT). The self-assembling monolayer(s) is made up of a plurality of assembly molecules each having an attaching group. For attaching to silica, the attaching group may include a silicon atom with as many as four attachment sites, for example; siloxanes, silazanes, and chlorosilanes. Alternative attaching groups include metal phosphate, hydroxamic acid, carboxylate, thiol, amine and combinations thereof for attaching to a metal oxide; thiol, amine, and combinations thereof for attaching to a metal; and chlorosilane for attaching to a polymer. A carbon chain spacer or linker extends from the attaching group and has a functional group attached to the end opposite the attaching group.

Methods of attaching and constructing the self-assembling monolayer on a mesoporous material involve solution deposition chemistry in the presence of water. More specifically, as reported by Feng, X.; Fryxell, G. E.; Wang, L. Q.;

Kim, A. Y.; Liu, J.; Kemner, K. *Science*, 1997, 276, 923-926 (Feng et al, 1997); and Liu, J.; Feng, X.; Fryxell, G. E.; Wang, L. Q.; Kim, A. Y.; Gong, M. *Adv. Mat.* 1998, 10, 161-165 (Liu et al., 1998), a synthetic protocol to prepare monolayers of MPTMS (mercaptopropyl trimethoxysilane) within the pores of MCM-41

5 involved a 1-hour hydration step, followed by a 6-hour silanation step in refluxing toluene. At this stage, the silane coverage is limited to approximately 3.6-4.0 silane molecules/nm² (this surface density is not enhanced by either extending the reaction time or increasing silane concentration). Following the silanation with a 2-3 hour azeotropic distillation drives the equilibria through the removal of
10 reaction by-products, and increases this surface density to 5.0-5.2 silanes/nm². This surface density is representative of typical silane-based monolayers. The monolayer coated mesoporous product is then isolated by filtration, washed extensively and then dried for several days. In summary, the overall procedure takes about 10 hours of laboratory prep time and 1-10 days of drying time. The
15 time is driven by the kinetics of getting the self-assembling molecules into the mesopores and getting the water and any other solvent out of the mesopores.

The product obtained exhibits a maximum of 40% of the monolayer silicon atoms fully crosslinked for maximizing monlayer stability. Ideally, 100% of the silicon atoms would be fully crosslinked. Full crosslinking is having three of the
20 four bonding sites linked to another silicon atom via an oxygen atom, with the fourth linked to the functional group terminated hydrocarbon chain. However, the presence of "dangling" hydroxyl groups (OH-) cannot be avoided in the solution method and it is the presence of the "dangling" hydroxyl groups that interferes with the crosslinking of the monolayer, thus placing a practical upper limit on the
25 number of silicon atoms that are fully crosslinked of 40%.

Thermal "curing" of silane monolayers, wherein typical thermal curing (ca. 150°C), of a silane monolayer creates a terminal to internal silane ratio of 1:2 corresponding to about 60% to 65% of attaching molecules (silicon) fully crosslinked.

30 Hence, there remains a need for a mesoporous material having self-assembling monolayer thereon with a greater fraction of the assembly atoms fully crosslinked. There is also a need for greater surface density of silicon

atoms, which may also be expressed as a greater surface density of monolayer coverage. Finally, there is a need for a method of making these materials that is less time consuming.

The main difficulty in functionalizing microporous materials may be attributed to diffusion of the organic molecules into the small pore channels. In the last few years, both post-silanization and *in-situ* deposition have been successfully applied to mesoporous materials, in which the pore diameter is usually larger than 2 nm. The mesoporous materials (usually synthesized using surfactant micelles as templates) have very uniform pore sizes. Because of their high surface area and the open pore channels; functionalized mesoporous materials have been investigated for many adsorption and catalysis applications. However due to the large pore size and the amorphous nature of the materials, these materials are not likely to find application as size selective catalysts.

A zeolite is any one of a family of hydrous aluminum silicate minerals, whose molecules enclose cations of sodium, potassium, calcium, strontium, or barium, or a corresponding synthetic compound, used chiefly as molecular filters and ion-exchange agents. Compared to the mesoporous materials, the diffusion of organic molecules in zeolites is severely hindered by the small pore size. Deposition of silanes on the exterior surface is therefore greatly favored over silanation of internal surfaces. Heretofore, it had been believed that introducing organic functional groups to the internal pore surfaces of commercial zeolites to produce size selective microporous catalysts could not be achieved due to the size of the pores.

SUMMARY OF THE INVENTION

According to the present invention, the previously known functional material having a self-assembled monolayer on a substrate has a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites wherein a bonding fraction (or fraction) of fully bonded assembly atoms (fully crosslinked assembly atoms) with the plurality of bonding sites (the plurality of bonding sites bonded to an oxygen atom) exceeds a maximum compared to

solution deposition, and maximum surface density of assembly molecules greater than for solution deposition. For example, with the assembly atom silicon, having 4 bonding sites, the bonding fraction maximum for solution deposition was 40% as deposited or about 60% to 65% (a terminal to internal
5 silane ratio of about 1:2) after thermal curing, and maximum surface density of silane molecules was 5.2 silanes per square nanometer. Note that crosslinking fraction and surface density are separate parameters.

The method of the present invention is an improvement to the known method for making a self-assembled monolayer on a substrate, wherein instead
10 of a liquid phase solution chemistry, the improvement is a supercritical phase chemistry.

The present invention has the advantages of greater fraction of bridging oxygen bonds, and greater surface density of assembly molecules resulting in a lower defect coating that enhances thermal and chemical stability or resistance.
15 Further, hydrolysis and deposition is complete within 5 minutes, a surprising rate enhancement of more than two orders of magnitude. Not only are the hydrolysis and deposition considerably accelerated relative to standard solution methods, but the final drying phase has been completely eliminated by the use of a supercritical fluid as the reaction medium. The product emerges from the
20 reaction chamber dry and ready to use. This represents considerable timesavings.

Water is a necessary reactant in the hydrolysis and condensation chemistry of alkylsilanes to form self-assembled monolayers onto ceramic oxide surfaces. It must be present in appropriate (stoichiometric) amounts; too little will
25 result in incomplete deposition and crosslinking and too much will result in bulk solution phase polymer formation. Experience has shown that approximately 10^{13} water molecules per square meter of available surface area is optimum. This amounts to approximately 2 water molecules for each silane to be anchored.

30 It is also important that this water be intimately associated with the surface and not free in solution. By having the water in close proximity to the ceramic oxide surface, the silane hydrolysis/condensation chemistry can only take place

on the surface, thereby favoring the desired monolayer deposition and avoiding solution phase polymerization (which leads to bulk amorphous polymer and blocked pores). This association is necessary to obtain any thin film morphology, and is critical to obtain clean monolayer formation.

5 In addition, the water associated with the ceramic oxide surface must be evenly spread out across the surface. This causes the hydrolysis chemistry to be uniformly spread out across the ceramic oxide surface, which reduces monolayer defect formation, while at the same time minimizing bulk polymerization.

10 By adding the water first, and allowing it to fully equilibrate with the ceramic oxide surface, Applicants are able to exploit the natural affinity that these ceramic oxides have for water and are thus able to insure that these important conditions are met.

 Adding water separately to a solution of silanes will result in bulk solution
15 phase polymerization competing with any possible monolayer deposition. This is counter-productive since it significantly depletes the amount of silane available to form the monolayer, and in the case of a mesoporous substrate, the bulk amorphous polymer will plug and block the pore channels, reducing the available surface area and restricting interfacial access, thus eliminating the most
20 desirable features of such a material.

 In the liquid solution deposition of the prior art, a wastestream is produced as a mixture of water, methanol, toluene and small amounts of mercaptan that failed to be deposited. It is impractical to separate this mixture, and therefore the mixture is usually disposed of as hazardous waste. According to the present
25 invention using a supercritical fluid for solution deposition, the only by-product of the reaction (hydrolysis) is an alcohol (e.g. methanol), which is easily separated from the supercritical fluid (which can be recovered for recycling). In fact, the alcohol is of sufficient purity to represent a potential feedstock that can be sold or recycled.

30 A further advantage of using a supercritical fluid as the reaction medium is the elimination of flammable solvents, and performing the reaction under

completely non-flammable conditions, which can be a significant concern upon scale-up.

The subject matter of the present invention is particularly pointed out and distinctly claimed in the concluding portion of this specification. However, both
5 the organization and method of operation, together with further advantages and objects thereof, may best be understood by reference to the following description taken in connection with accompanying drawings wherein like reference characters refer to like elements.

10 BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a graph of percent composition versus time for the hydroxylated silanol.

15 FIG. 2a is an NMR spectrum of a 5-minute sample made according to the present invention.

FIG. 2b is an NMR spectrum of a 24-hour sample made according to the present invention.

FIG. 2c is a peak ratio (percent) versus time for various samples.

20 FIG. 3 is an NMR spectrum of a 5-minute sample re-annealed for 30 minutes.

FIG. 4 is a graph of sulfur concentration versus pH for samples made according to the present invention and compared to samples made by solution deposition exposed to corrosive solutions.

25 DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

30 According to the present invention, the previously known functional material having a self-assembled monolayer on a substrate, the self-assembled monolayer having a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites wherein a portion of the assembly atoms have the plurality of bonding sites bonded to an oxygen atom is improved so that a

greater portion of the assembly atoms have the plurality of bonding sites bonded to an oxygen atom.

In addition, the known functional material having a self-assembled monolayer on a substrate having a surface density by liquid solution deposition
5 of the self-assembled molecules is improved so that the surface density is greater.

The method of the present invention is an improvement to the known method for making a self-assembled monolayer on a substrate, the self-assembled monolayer having a plurality of assembly molecules each with an
10 assembly atom with a plurality of bonding sites, the method having the step of bonding a plurality of oxygen atoms to a fraction of the plurality of bonding sites; wherein the improvement is the bonding done by preparing the self-assembled monolayer in a supercritical fluid.

The supercritical fluid may be polar or non-polar. Compounds useful in
15 the supercritical phase according to the present invention included carbon dioxide, and possibly freons, nitrogen, noble gases, alkanes, alkenes, alkynes, and combinations thereof.

The thermal curing of the self-assembled monolayer may be during or after forming of the self-assembled monolayer. In other words, a self-assembled
20 monolayer that has been prepared in a supercritical fluid exhibiting a portion of assembly atoms fully crosslinked to oxygen atoms and a maximum surface density of assembly atoms may be exposed to a supercritical fluid for a time that is effective in converting interfering hydroxyl groups to bridging oxygen bonds, thereby increasing the number of fully crosslinked silicon atoms to a greater
25 portion. Alternatively, a self-assembled monolayer prepared by any other method, for example liquid solution chemistry, may be treated by adding assembly molecules to the gaps of the alternatively prepared monolayer. The assembly molecules are added in a supercritical fluid containing additional assembly molecules. The greater portion is at least about 75%, preferably
30 greater than or equal to 80%.

The assembly atoms are selected to be compatible with the substrate. For attaching to silica, the assembly atom may include a silicon atom with four

attachment sites, for example siloxane, silazane, and chlorosilane. Alternative assembly molecules include metal phosphate, hydroxamic acid, carboxylate, thiol, amine and combinations thereof for attaching to a metal oxide; thiol, amine, and combinations thereof for attaching to a metal; and chlorosilane for attaching to a polymer. A carbon chain spacer or linker may extend from the assembly atom and has a functional group attached to the end opposite the assembly atom.

For silicon atoms having four bonding sites, the portion of fully crosslinked bonding sites by supercritical fluid solution exposure including supercritical fluid solution deposition is greater than or equal to about 40% as deposited. Additional exposure time increases the fully crosslinked fraction to at least about 55%. Table 1 shows the amount of time for the percent of fully crosslinked siloxanes for supercritical fluid processing at 7500 psi and 150 °C. The times and percent of full crosslinking are pressure and temperature dependent.

TABLE 1 – Supercritical CO₂ Exposure Time for Percent of Fully Crosslinked Siloxanes

Time (hours)	% of Fully Crosslinked Siloxanes
≤ 1/12	> 40
4	55
24	75

In addition, supercritical fluid solution deposition results in greater surface density of the assembly molecules. For siloxane, the surface density is greater than 5.2 siloxane molecules per square nanometer, and has been demonstrated up to 6.5 siloxane molecules per square nanometer.

Alternatively, or additionally, the surface deposition of the self-assembling monolayer(s) may be done in a manner of placing one or more self-assembling monolayer precursor(s), including but not limited to alkoxysilane, silazane, chlorosilane, and combinations thereof, together with mesoporous material that may be ceramic, for example metal oxide, including but not limited to silica,

alumina, titania, and combinations thereof, in a vessel that is subsequently filled with a supercritical fluid, including but not limited to carbon dioxide (CO₂), ethane (C₂H₆), ammonia (NH₃), and combinations thereof, to obtain the self-assembling monolayer(s) on the mesoporous or zeolite material. By using a supercritical
5 fluid for deposition of the self-assembling monolayer, the surface density of silanes may be greater than 5.2 silanes per square nanometer. The surface density is controlled by the amount of assembly molecule (e.g. silane) used for a given surface area of mesoporous material. Moreover, deposition is complete in about 5 minutes and no subsequent drying is needed. With a 5-minute
10 deposition, the percent of fully crosslinked silicon atoms is about 40%. Additional supercritical fluid exposure time increases the percentage of fully crosslinked silicon atoms (see Table 1 above).

Further, the placing of the calcined mesoporous material may include mixing a sol-gel solution and surfactant for producing a mesoporous green body;
15 removing the surfactant with the supercritical fluid and making a dry green body; and calcining said dry green body into the claimed mesoporous material. In this manner, the entire process from sol-gel templating through self-assembling monolayer deposition to increasing the fraction of fully bonded silicon atoms may be done in a single vessel in a supercritical fluid environment.

20

Example 1

An experiment was conducted to test the influence of supercritical carbon dioxide (SCCO₂) on the hydration of a mesoporous silica designated MCM-41, obtained by making the MCM-41 according to U.S. patent 5,264,203 (Mobil Oil
25 Corporation, Fairfax, VA). The calcined substrate (primarily Q4 [non-hydroxylated silanol]) was free of any silane(s).

Water was introduced to the pores of the MCM-41 sample *via* passive hydration in a 100% humidity chamber, followed by subjecting the hydrated sample to SCCO₂ forced hydrolysis at 100°C. This hydration protocol involved
30 neutral pH, no salt, no ceramic oxide or organic contaminants; just water, carbon dioxide and heat.

NMR analysis showed that this hydrolysis treatment was found to increase the bonding fraction (hydroxylated silicon atoms) to 46% Q3 (surface silanol) and 8% Q2 (geminal silanol). This hydrolysis was carried out in the presence of excess water and hydrolysis stopped at this point, with no damage to the mesostructure. The mild conditions of this hydrolysis prevent the dissolution of the MCM-41 since silicic acid is insoluble in SCCO_2 , and thus there was very little risk of collapsing the mesostructure. (SCCO_2 is very nonpolar, and approximates hexane in its solvating power).

The hydrolysis reaction was complete in about 20 minutes (See FIG. 1).

A comparison was made to a hydration or hydrolysis done by placing a second sample of MCM-41 in water and boiling at atmospheric pressure for 4 hours. In this comparison, no change or difference was observed.

Example 2

An experiment was conducted to compare the surface density of assembly molecules using prior liquid solution deposition as reported by Feng et al., 1997 and Liu et al, 1998 (described in Background above), and using the supercritical fluid solution deposition of the present invention.

Surface density was determined gravimetrically and by ^{29}Si NMR.

The surface density of the product made with the liquid solution deposition which included an azeotropic distillation was 5.0-5.2 silanes/ nm^2 .

According to the present invention, The silica was hydrated by simply storing it in a 100% humidity chamber and monitoring the sample's weight as a function of time, stopping at 20-25% weight gain. The MCM-41 was added to the sample holder along with the MPTMS (mercaptopropyl trimethoxysilane), then the system was sealed and brought up to pressure and temperature (7500 psi and 150°C) with SCCO_2 . After only 5 minutes, a monolayer with a surface density of 6.4 silanes/ nm^2 was deposited which was surprisingly approximately 20% higher than achieved using liquid phase deposition.

The spectrum of this 5-minute sample is shown in FIG. 2a. A reference peak 200 is from TTMS tetrakis (trimethylsilyl) silane. The peak 202 is a combination of signals for Q2, Q3, and Q4 silicic acid units in the base material.

The peaks 204, 206, 208 are the internal, terminal, and isolated silanes respectively. The silane demographics of this sample are similar to those found in monolayers prepared under atmospheric pressure and liquid solution phase conditions.

5 It was also found that maintaining the sample at elevated temperature and pressure in SCCO₂ resulted in a slow but steady evolution of the silane demographics, with a gradual decrease in the population of the terminal silane with a concomitant increase in the population of the internal silane over 24 hours. Over this same timeframe, the signal for the isolated silane completely
10 disappeared, indicating an annealing of the "dangling" hydroxyls within the monolayer, resulting in a greater fully bonded fraction or higher degree of siloxane cross-linking. In this experiment, we observed a terminal to internal silane ratio (based upon total area under each peak) of approximately 1:4 after 24 hours (FIG. 2b). This is unexpectedly the highest degree of crosslinking in a
15 silane based monolayer documented by ²⁹Si NMR. Ratios as a function of time are summarized in FIG. 2c showing evolution of silane demographics.

Both the surprising surface density and the unexpected high degree of crosslinking are directly attributable to the use of SCCO₂ as the reaction medium.

20

Example 3

An experiment was conducted as in Example 2 wherein a portion of the material from the 5-minute sample was re-exposed or re-introduced to the supercritical fluid environment for an additional 30 minutes.

25 Results are shown in FIG. 3. The evolution or formation of the monolayer continued in the same manner as for continuous supercritical fluid exposure.

Example 4

30 An experiment was conducted to demonstrate the enhanced chemical stability of the coating material as produced as in Example 2. Samples of the coating material of the present invention from Example 2 were exposed to a series of identical buffer solutions of various pH. Comparative samples of

solution deposited coating material were exposed to identical buffer solutions of various pH from pH 0.5 to pH 12.5.

Results are shown in FIG. 4 wherein essentially no difference is observed for pH less than 9, but above pH 9 up to pH 12.5, the solution deposited material (Regular SAMMS) exhibits a leaching or loss of sulfur to the solution indicating a degradation of the monolayer. The supercritical deposited material according to the present invention shows no change in sulfur concentration above pH 9 up to pH 12.5. This increase in chemical durability of the monolayer is an unexpected result.

Example 5

An experiment was conducted as in Example 2 wherein Zeolite beta from (Zeolyst) in the form of beads (3 mm in diameter) was mixed with tris(methoxy)mercaptopropylsilane (TMMPS) with a zeolite to TMMPS weight ratio of 0.67 and loaded into the sample container in the supercritical reaction vessel. The system was sealed. The pressure and the temperature were increased to 7500 psi and 150 °C using CO₂. The zeolite was treated under these conditions for 12 hours before the pressure was reduced and temperature decreased to 25 °C. The treated zeolite beads were recovered after the treatment, and ground into powders for further treatment.

Functionalized and unfunctionalized zeolites were characterized by X-ray diffraction (XRD). The XRD peaks recorded are consistent with the XRD data reported for zeolite beta, but the diffraction peaks are broader and weaker. Apart from the two main peaks at 2 theta of 7.7° and 22.5°, other minor diffraction peaks are not well resolved. The XRD data suggest that the commercial zeolite beta used here has a similar crystalline structure as the synthetic high purity zeolite beta, but has smaller crystallite size, or a higher degree of disordering. Transmission electron microscopy (TEM) images and electron energy dispersive X-ray spectroscopy (EDX) spectra were also obtained. Because the commercial zeolite beta is not highly crystalline, the zeolite lattice fringes are not resolved in the TEM image. In the EDX spectrum, a strong Si peak, a small Al peak (from the zeolite material), and a small S peak is observed. This S peak comes from

the sulfonate group introduced into the zeolites during SCCO_2 functionalization. From the EDX data the sulfonate group density in zeolite can be estimated to be 0.87 mmol sulfonate/g zeolite. The aluminum concentration is about 2% by weight.

5 Typically part of the unreacted silanes and by-products would be forced out of the inner volume of the porous substrate when the pressure was quickly reduced in the supercritical treatment. After the supercritical treatment, the materials were further treated with H_2O_2 / method solutions and H_2SO_4 solutions over long periods of time during the acidifying and sulfonation procedure, which
10 also includes many washing and rinsing steps involving ethanol and water. It is expected that any physically trapped silanes or its by-products should be removed from the material during these treatments. This conclusion is verified by acid washing experiments. No silane product was released, as measured by NMR experiment, when the sulfonated zeolite was subject to extended wash in
15 0.1 M acid solutions.

A Chemagnetics NMR spectrometer was used to obtain ^{29}Si NMR results. It is important to recognize that relative peak intensities in ^{29}Si CP-MAS are not strictly quantifiable due to differences in relaxation behavior. Therefore, we have used the Bloch decay pulse sequence (single pulse excitation) with long recycle
20 times (30 sec) to obtain the spectrum more representative of the molecular composition of these materials. The large peak at -110 ppm is from the silica support. The broad feature at -110 ppm is also indicative of the poor crystalline nature of the zeolite. Two additional peaks from -50 to -80 ppm corresponding to siloxane groups in the functionalized zeolites are observed. The siloxanes peaks
25 are much more pronounced than reported in literature, suggesting a higher surface coverage. The peak positions suggest a high degree of crosslinking between the siloxane groups, and between siloxane groups and the substrate. Since the small pore size excludes the possibility of close packing of the silane groups, so most likely the siloxanes are attached to the substrate with a
30 tridentate, or bidentate binding. On smooth substrates or in large pore materials, both tridentate and bidentate bindings are not favored. This binding scheme has been reported in zeolites because of the small pore size and high curvature.

The conversion of HEX and PYC can be easily quantified and the only observed products were the mixtures of reactants and acetalized (or ketalized) products. For sulfonated zeolite (Z-SO₃H), more than 60 % HEX was converted in 4 hours, and nearly complete conversion was observed over 12 hours. On the other hand, PYC, which has a large molecular size and cannot enter the microporosity, showed less than 8 % conversion over extended reaction time with same Z-SO₃H as catalyst. These results indicate that the Z-SO₃H material is size selective, and that the majority of SO₃H groups are inside the microporosity and are accessible to molecules smaller than the pore size, and inaccessible to the molecules larger than the pore size. The reaction rate with SCCO₂ Z-SO₃H compares favorably with similar zeolite functionalized using an *in-situ* deposition technique, which produced 38 % conversion of HEX in 4 hours under the same conditions. Both HEX and PYC were also reacted over pure zeolite beta (Z), and the TMMPS functionalized zeolite (Z-SH) before it was treated with H₂O₂. Pure zeolite and Z-SH showed low catalytic activity, and only a small fraction of either HEX and PYC was converted. It can be concluded from these results that the majority of SO₃H groups reside inside the zeolite pore channels and act as the active center for the reaction. It is important to note that no additional extraction procedure was performed on the supercritically processed zeolite to remove chemically bonded sulfonated groups on the external surface of the zeolite. Therefore a small portion of chemically bonded sulfonated groups remained on the external surface, which gave rise to the residual activity observed for PYC. However, the contribution of the external sulfonic groups to the overall reaction is minimal. Furthermore, the activity of the external acid groups can be selectively neutralized to achieve complete size selectivity (which has been demonstrated in our experiments). The external acid groups can be also removed through a post extraction treatment.

The high activity of the functionalized zeolite over the parent material is attributed to the acidic groups introduced by the functional groups. To verify this, acid-base titration was conducted to determine the number of acid sites. The titration was conducted in 5.0 ml 0.1 N HCl solution with 0.05 g suspended solid powders using a 0.1 N NaOH solution as the titrant. The titration curve is the

superposition of the titration curve of the strong acid (HCl) and that of the surface acid group from the catalyst. The proton capacity (acid site density) can be calculated using standard methods. The titration experiments showed that the sulfonated zeolites (Z-SO₃H) have a much high proton capacity (25.7 mmol/g) as
5 compare with the native zeolite beta (3.79 mmol/g) and the unsulfonated thiol zeolite (Z-SH) (3.37 mmol/g).

For comparison, sulfonated mesoporous silica (M-SO₃H) was used to catalyze the conversion of PYC and HEX. In this case both HEX and PYC can easily enter the pore channel and access the catalytic SO₃H-sites. Therefore
10 low-selective conversion of both HEX and PYC were observed.

Further evidence of the size selectivity is provided when amines of different sizes are used to poison (neutralize) the acid sites. Reaction of HEX and glycol was performed over Z-SO₃H as discussed before. Triethylamine ((C₂H₅)₃N, or TEA) is added to the reaction bath after 40 minutes. TEA is a small
15 molecule and can enter the microporosity and poison all the acid sites. The addition of TEA completely stopped the reaction. Under the same condition the addition of methyldioctylamine [(CH₃(CH₂)₇)₂NCH₃, or MDOA] instead of TEA did not have any effect on the conversion of HEX over Z-SO₃H, because the molecular size of MDOA is too large for it to enter the microporosity and poison
20 the acid sites in the internal pore channels. The addition of MDOA did effectively neutralize all the residual acid sites on the external surfaces of Z-SO₃H. Zero activity was observed for PYC under these conditions. If the pore size is large enough, like in mesoporous silica (M-SO₃H), MDOA is an effective poison for acid catalyzed reaction. We have shown that the addition of MDOA to the
25 reaction bath of HEX over M-SO₃H completely stopped the reaction in the mesoporous materials.

CLOSURE

30 While a preferred embodiment of the present invention has been shown and described, it will be apparent to those skilled in the art that many changes and modifications may be made without departing from the invention in its

broader aspects. The appended claims are therefore intended to cover all such changes and modifications as fall within the true spirit and scope of the invention.

CLAIMS

We claim:

- 5
1. A functionalized material having a self-assembled monolayer on a substrate said self-assembled monolayer having a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites wherein a portion of fully crosslinked silicon atoms is a maximum portion provided by a liquid solution deposition; wherein the improvement comprises:
- 10 said portion of fully bonded silicon atoms is greater than said maximum portion as provided by supercritical fluid solution exposure.
2. The functionalized material as recited in claim 1, wherein said assembly atom is silicon having four bonding sites and said maximum portion is 40%.
- 15 3. The functionalized material as recited in claim 2, wherein said greater portion is greater than 55%.
- 20 4. The functionalized material as recited in claim 3, wherein said greater portion is greater than or equal to about 75%.
5. The functionalized material as recited in claim 1, wherein a surface density of said plurality of assembly molecules is greater than 5 assembly molecules per square nanometer.
- 25 6. The functionalized material as recited in claim 5, wherein said surface density is about 6.5 assembly molecules per square nanometer.
- 30 7. A functionalized material having a self-assembled monolayer on a substrate said self-assembled monolayer having a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites wherein

a surface density of said assembly molecules is a maximum surface density provided by liquid solution deposition; wherein the improvement comprises:

said surface density is a greater surface density greater than said maximum surface density as provided by supercritical fluid solution deposition.

5

8. The functionalized material as recited in claim 7, wherein said maximum surface density is less than or equal to 5 assembly molecules per square nanometer, and said greater density is greater than 5 assembly molecules per square nanometer.

10

9. The functionalized material as recited in claim 7, wherein said plurality of assembly molecules has a greater portion of fully bonded assembly atoms greater than a portion of fully bonded assembly atoms.

15

10. The functionalized material as recited in claim 9, wherein said greater portion of fully bonded silicon atoms is greater than 55%.

20

11. The functionalized material as recited in claim 10, wherein said greater portion of fully bonded silicon atoms is greater than or equal to about 75%.

12. The functionalized material as recited in claim 7, wherein said substrate is a mesoporous material.

25

13. A method of making a self-assembled monolayer on a substrate said self-assembled monolayer having a plurality of assembly molecules each with an assembly atom with a plurality of bonding sites, the method having the step of bonding a plurality of oxygen atoms to a fraction of said bonding sites; wherein the improvement comprises:

30

said bonding is by exposing said self-assembled monolayer to supercritical fluid.

14. The method as recited in claim 13, wherein said supercritical fluid is carbon dioxide.

15. The method as recited in claim 13, wherein said exposing is for a time of at least 5 minutes.

16. The method as recited in claim 15, wherein said exposing is for a time of at least 4 hours.

17. The method as recited in claim 16, wherein said exposing is for a time of about 24 hours.

18. The method as recited in claim 13, wherein said exposing comprises:

placing a self-assembled monolayer precursor together with a calcined mesoporous material into a vessel; followed by introducing a supercritical fluid into said vessel for a time and depositing said self-assembled monolayer onto said calcined mesoporous material.

19. The method as recited in claim 18, wherein said placing said calcined mesoporous material comprises: mixing a sol-gel solution and surfactant for producing a mesoporous green body;

removing said surfactant with said supercritical fluid and making a dry green body;

calcining said dry green body into said calcined mesoporous material.

20. A functionalized porous material comprising a substrate, a monolayer deposited on said substrate having a plurality of assembly molecules each with a plurality of assembly atoms having a plurality of bonding sites; and

said assembly atoms being greater than 70% fully cross linked with cross linking atoms.

21. The material of claim 20, wherein the substrate is a porous ceramic material.

22. The material of claim 21, wherein a pore size of said ceramic porous material is greater than 5 Å (angstroms).

23. The material of claim 20, wherein said assembly atom is silicon.

24. The material of claim 20, wherein said assembly molecules are selected from the group consisting of metal phosphate, hydroxamic acid, carboxylate, thiol, amine and combinations thereof for attaching to a metal.

25. The material of claim 20, wherein said assembly molecules comprises chlorosilane for attaching to a polymer.

26. The material of claim 20, wherein the monolayer comprises a surface density of assembly atoms greater than 6.4 silanes/nm².

27. The material of claim 20, wherein the cross linking atom is oxygen.

28. A method of functionalizing a porous material comprising the steps of

- a) hydrating a porous substrate;
- b) placing said hydrated porous substrate into a vessel in the presence of a precursor comprising assembly atoms and cross linking atoms;
- c) sealing the sample holder;

- d) introducing a supercritical fluid into said vessel for a time while increasing the pressure and temperature within said vessel to a supercritical pressure and temperature;
- 5 e) maintaining the porous substrate within said vessel under supercritical conditions for a time sufficient to fully cross link at least 70% of said assembly atoms with said cross linking atoms on the exposed surface of said materials.

10 29. The method of claim 28, whereby said porous substrate is ceramic.



30. The method of claim 29, whereby said ceramic porous substrate comprises pores having a diameter greater than 5Å.

15 31. The method of claim 28, whereby hydrating said porous substrate is provided by a humidity chamber having a humidity of 100%.



32. The method of claim 28, whereby said assembly atom is silicon.

20 33. The method of claim 28, whereby said supercritical fluid is carbon dioxide (CO₂), ethane (C₂H₆), ammonia (NH₃), and combinations thereof.



1/3

*Fig. 1**Fig. 2A*

2/3

*Fig. 2B**Fig. 2C*

3/3

*Fig. 3**Fig. 4*

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/US 00/07684

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J31/02 B01J37/00 B01J29/06 C01B39/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 725 987 A (COMBES JAMES R ET AL) 10 March 1998 (1998-03-10) claims 1-25 column 4, line 50 - line 55 example II	13-15, 28-30, 32,33
X	PATENT ABSTRACTS OF JAPAN vol. 018, no. 061 (C-1160), 2 February 1994 (1994-02-02) & JP 05 279011 A (MATSUSHITA ELECTRIC WORKS LTD), 26 October 1993 (1993-10-26) abstract -/-	13,14

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

25 July 2000

Date of mailing of the international search report

02.08.00

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Zuurdeeg, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/07684

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	CHUNTAO CAO AND THOMAS J. MCCARTHY: "Formation of trialkyl silyl monolayers on Si(100) using organosilanes in carbon dioxide" POLYMER PREPRINTS, vol. 40, no. 2, 2 August 1999 (1999-08-02), page 841-842 XP000925646 AMERICAN CHEMICAL SOCIETY, US ISSN: 0032-3934	13-16
A	the whole document	28,29, 32,33
A	WO 98 34723 A (BATTELLE MEMORIAL INSTITUTE) 13 August 1998 (1998-08-13) cited in the application claims 14-38	13-19, 28-33

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 00/07684

Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 1-12, 20-27
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 00 07684

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 1-12, 20-27

Present claims 1-12 and 20-27 relate to a compound defined (inter alia) by reference to the following parameters:

- *) a portion of fully bonded silicon atoms as provided by supercritical fluid solution exposure is greater than a maximum portion of fully crosslinked silicon atoms provided by a liquid solution deposition
- *) a surface density of assembly molecules as provided by supercritical fluid solution exposure is greater than a maximum surface density of assembly molecules provided by a liquid solution deposition
- *) assembly atoms being greater than 75% fully crosslinked with crosslinking atoms

The use of these parameters in the present context is considered to lead to a lack of clarity within the meaning of Article 6 PCT. It is impossible to compare the parameters the applicant has chosen to employ with what is set out in the prior art. The lack of clarity is such as to render a meaningful complete search impossible. Furthermore there are 3 independant product claims defined by the different parameters; it is not clear for what the applicant seeks protection. Consequently, the search has been restricted to the method of preparing of the functionalized porous material, claims 13-19, and 28-33.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/07684

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5725987 A	10-03-1998	JP 10133417 A	22-05-1998
JP 05279011 A	26-10-1993	JP 2659155 B	30-09-1997
WO 9834723 A	13-08-1998	EP 0969922 A	12-01-2000